
	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	ACRILONITRILE BUTADIENE STYRENE "ABS"	WWW.TPCO.IR	
	HR2320	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (200°C/5KG)	g/10min	ASTM D-1238	0.9-1.5
IZOD IMPACT STRENGTH (NOTCHED 1/4 INCH@25°C)	KJ/M2	ASTM D-256	MIN 17

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.


TABRIZ PETROCHEMICAL CO

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	ACRILONITRILE BUTADIENE STYRENE "ABS"	WWW.TPCO.IR	
	HR2340	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (200°C/5KG)	g/10min	ASTM D-1238	0.7-1.3
IZOD IMPACT STRENGTH (NOTCHED 1/4 INCH@25°C)	KJ/M2	ASTM D-256	MIN 38

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.


TABRIZ PETROCHEMICAL CO

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	ACRILONITRILE BUTADIENE STYRENE "ABS"	WWW.TPCO.IR	
	HR0370	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (200°C/5KG)	g/10min	ASTM D-1238	0.9 - 1.4
IZOD IMPACT STRENGTH (NOTCHED 1/4 INCH@25°C)	KJ/M2	ASTM D-256	14 - 20

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.


TABRIZ PETROCHEMICAL CO

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	ACRILONITRILE BUTADIENE STYRENE "ABS"	WWW.TPCO.IR	
	SD0140	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (200°C/5KG)	g/10min	ASTM D-1238	2.9-3.6
IZOD IMPACT STRENGTH (NOTCHED 1/4 INCH@25°C)	KJ/M2	ASTM D-256	MIN 20

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.


TABRIZ PETROCHEMICAL CO

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	ACRILONITRILE BUTADIENE STYRENE "ABS"	WWW.TPCO.IR	
	SD0150	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (200°C/5KG)	g/10min	ASTM D-1238	1.4-2.2
IZOD IMPACT	KJ/M2	ASTM D-256	19-25

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.


TABRIZ PETROCHEMICAL CO

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	ACRILONITRILE BUTADIENE STYRENE "ABS"	WWW.TPCO.IR	
	SD0152	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (200°C/5KG)	g/10min	ASTM D-1238	2-2.8
IZOD IMPACT	KJ/M2	ASTM D-256	19-26

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.


TABRIZ PETROCHEMICAL CO

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	ACRILONITRILE BUTADIENE STYRENE "ABS"	WWW.TPCO.IR	
	SV0157	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (200°C/5KG)	g/10min	ASTM D-1238	0.3-0.9
IZOD IMPACT	KJ/M2	ASTM D-256	24-35

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.


TABRIZ PETROCHEMICAL CO

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	ACRILONITRILE BUTADIENE STYRENE "ABS"	WWW.TPCO.IR	
	SH0150	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (200°C/5KG)	g/10min	ASTM D-1238	0.8 - 1.4
IZOD IMPACT	KJ/M2	ASTM D-256	19-25

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.


TABRIZ PETROCHEMICAL CO

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	ACRILONITRILE BUTADIENE STYRENE "ABS"	WWW.TPCO.IR	
	VH0800D	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (200°C/5KG)	g/10min	ASTM D-1238	4.7 - 7
IZOD IMPACT	KJ/M2	ASTM D-256	12 - 19

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.

TABRIZ PETROCHEMICAL CO

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	ACRILONITRILE BUTADIENE STYRENE "ABS"	WWW.TPCO.IR	
	HM0560	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (200°C/5KG)	g/10min	ASTM D-1238	2 - 3
IZOD IMPACT	KJ/M2	ASTM D-256	10 - 16

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.

TABRIZ PETROCHEMICAL CO