
	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	May-2021
	POLYETHYLENE	WWW.TPCO.IR	
	LL0209AA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	0.8-1
DENSITY	gr/cm3	ASTM D-1505	0.918-0.921
CONTAMINATION	NO.	BP137	≤4 DEFECTS IN 200GR OF PELLETS

***FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS**


TABRIZ PETROCHEMICAL

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	May-2021
	POLYETHYLENE	WWW.TPCO.IR	
	LL0209KJ	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	0.8-1
DENSITY	gr/cm3	ASTM D-1505	0.918-0.921
CONTAMINATION	NO.	BP137	≤4 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	LL0205AA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	0.4-0.6
DENSITY	gr/cm3	ASTM D-1505	0.919-0.923
CONTAMINATION	NO.	BP137	≤4 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	LL0205KJ	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	0.4-0.6
DENSITY	gr/cm3	ASTM D-1505	0.919-0.923
CONTAMINATION	NO.	BP137	≤4 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	LL0220AA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	2-2.5
DENSITY	gr/cm3	ASTM D-1505	0.919-0.923
CONTAMINATION	NO.	BP137	≤4 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	LL0220KJ	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	2-2.5
DENSITY	gr/cm3	ASTM D-1505	0.919-0.923
CONTAMINATION	NO.	BP137	≤4 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	LL0410AA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	0.9-1.1
DENSITY	gr/cm3	ASTM D-1505	0.924-0.928
CONTAMINATION	NO.	BP137	≤4 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	LL0640AA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	3.8-4.5
DENSITY	gr/cm3	ASTM D-1505	0.929-0.932
CONTAMINATION	NO.	BP137	≤4 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD3840UA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	3.8-4.5
DENSITY	gr/cm3	ASTM D-1505	0.935-0.939
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD4005EA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	0.4-0.6
DENSITY	gr/cm3	ASTM D-1505	0.938-0.940
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD4440EA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL: +984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	3.7-4.4
DENSITY	gr/cm3	ASTM D-1505	0.942-0.946
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	March-2021
	POLYETHYLENE	WWW.TPCO.IR	
	HD5030SA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	1.7-1.9
DENSITY	gr/cm3	ASTM D-1505	0.946-0.949
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	March-2021
	POLYETHYLENE	WWW.TPCO.IR	
	HD5030EA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	1.7-1.9
DENSITY	gr/cm3	ASTM D-1505	0.946-0.949
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD5211EA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	10-12
DENSITY	gr/cm3	ASTM D-1505	0.951-0.953
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD5218UA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL: +984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	17-19
DENSITY	gr/cm3	ASTM D-1505	0.951-0.953
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD5218EA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	17-19
DENSITY	gr/cm3	ASTM D-1505	0.951-0.953
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD5813EA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	12.1-14.1
DENSITY	gr/cm3	ASTM D-1505	0.952-0.956
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD5813UA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	12.1-14.1
DENSITY	gr/cm3	ASTM D-1505	0.952-0.956
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD5406EA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	0.5-0.7
DENSITY	gr/cm3	ASTM D-1505	0.952-0.955
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD6040UA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	3.5-4.3
DENSITY	gr/cm3	ASTM D-1505	0.956-0.960
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD6070UA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	6.8-7.5
DENSITY	gr/cm3	ASTM D-1505	0.956-0.960
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS


TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD6070EA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	6.8-7.5
DENSITY	gr/cm3	ASTM D-1505	0.956-0.960
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS

TABRIZ PETROCHEMICAL COMPANY

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	June-2020
	POLYETHYLENE	WWW.TPCO.IR	
	HD3808EA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	0.5-0.8
DENSITY	gr/cm3	ASTM D-1505	0.937-0.940
CONTAMINATION	NO.	BP137	≤5 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS

TABRIZ PETROCHEMICAL COMPANY